

MINING / CONSTRUCTION

Tekseal™ S

LOW DENSITY CEMENT FOAM

DESCRIPTION

Tekseal™ S powder is supplied in 25kg lined woven polypropylene bags. It forms cement foam on mixing with water in a purpose designed placer.

APPLICATION AND USE

Tekseal™ S is used for void filling where longer flow distances and good penetration of loose fallen rock are required.

Typical applications of Tekseal S are:

- Cavity filling after falls of ground.
- Construction of ventilation walls.

ADVANTAGES

- High volume yield improves material handling logistics and cost
- Rapid placement reduces man shifts - typically 50m³ void filled per shift
- Remote placement can take place up to 100m from machine
- Typically only 3 people needed per crew
- Non-flammable, non-toxic, cement based



TECHNICAL DATA

MIX DATA

Details	Value
Relative Density (RD) Wet	0.35 - 0.45*
Water / solids ratio, w/s	0.8:1 - 1:1

* Depending on foam machine settings

COMPRESSIVE STRENGTH

Curing Age	Compressive strength
28 days Density = 0.35	0.35 MPa

PUMP LIFE / SET TIME

Maximum pump life is approximately 15 minutes with water at 25°C. Rate of set and strength development will depend on temperature and the water / solids ratio used.

APPLICATION METHOD

Tekseal™ S must only be placed using a purpose designed placer at the stipulated water: solids ratio. Tekseal™ S can be placed in remote areas via a 100m plastic or rubber pipe. Large cavities can be filled using standpipes.

All tools and equipment must be washed with water immediately after use.

Pack Size (kgs)	Mix Water (litres)	Volume Yield (litres)
25	20	128

SAFETY INSTRUCTIONS AND LIMITATIONS

Tekseal™ S is alkaline. The use of gloves and goggles is recommended. Splashes must be removed from the skin and eyes by washing with clean water. In case of splashes in the eyes, medical attention should be sought immediately. Refer to Material Safety Data Sheet.

PACKAGING AND TRANSPORTATION

Packed in 25 kg bags. Bags are stacked 40 per pallet and stretch-wrapped.

Bags may also be grouped into 1-tonne bulk bags upon request.

STORAGE AND SHELF LIFE

Store Tekseal™ S unopened in original bags in dry conditions. Storage outside these guidelines may impair shelf life of 12 months.

DISPOSAL

Follow local regulations.

DISCLAIMER

The Minova Logo is a registered trademark.

Copyright © 2019 Minova. All rights reserved

All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non-infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

ADDITIONAL DOCUMENTATION

- MSDS of Tekseal™ S

LIST OF REPRESENTATIVES

- AUSTRIA: Minova MAI GmbH
- CZECH REPUBLIC: Minova Bohemia s.r.o.
- FRANCE / BELGIUM: Sales office Minova France / Belgium
- GERMANY: Minova CarboTech GmbH
- ITALY: Minova CarboTech GmbH Italy branch
- KAZAKHSTAN: Minova Kazakhstan LLP
- POLAND: Minova Ekochem S.A.; Minova Arnall Sp. z o.o.; Minova Ksante Sp. z o.o.
- RUSSIA: ZAO "Carbo-ZAKK"
- SLOVAKIA: Minova Bohemia s. r. o., organizačná zložka
- SOUTH AFRICA: Minova Africa (Pty) Ltd.
- SPAIN: Minova Codiv S.L.U.
- SWEDEN / NORWAY: Minova Nordic AB
- UNITED KINGDOM: Minova Weldgrip Ltd.; Minova International Ltd.
- APAC: Minova Australia Pty Ltd.
- AMERICAS: Minova USA Inc.

CUSTOMER SERVICE

For additional support options available at your area, contact our local offices.

www.minovaglobal.com